

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : C07C 69/54, 69/78, 69/96, 69/533, C07D 303/22, 303/40, C09K 19/30, 19/38, C08F 20/18, C08G 59/20, 59/22</p>	A1	<p>(11) International Publication Number: WO 97/34862</p> <p>(43) International Publication Date: 25 September 1997 (25.09.97)</p>
<p>(21) International Application Number: PCT/EP97/00843</p> <p>(22) International Filing Date: 21 February 1997 (21.02.97)</p> <p>(30) Priority Data: 96104330.4 19 March 1996 (19.03.96) EP</p> <p>(34) Countries for which the regional or international application was filed: DE et al.</p> <p>(71) Applicant (for all designated States except US): MERCK PATENT GMBH [DE/DE]; Frankfurter Strasse 250, D-64293 Darmstadt (DE).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): COATES, David [GB/GB]; 87 Sopwith Crescent, Merlex Wimborne, Dorset BH21 1SW (GB). GREENFIELD, Simon [GB/GB]; 2 Blackbird Close, Creekmoor, Poole, Dorset BH17 7YA (GB). JOLLIFFE, Emma [GB/GB]; 48 The Woodpeckers, Broadway, Weymouth, Dorset DT3 5RS (GB). HASSALL, Ian, Victor [GB/GB]; 39 Priory View Road, Burton, Christchurch, Dorset BH23 7EU (GB). MAY, Alison [GB/GB]; 10 Hadrian Way, Corfe Mulen, Wimborne, Dorset BH21 3XF (GB).</p>		<p>(74) Common Representative: MERCK PATENT GMBH; Postfach, D-64271 Darmstadt (DE).</p> <p>(81) Designated States: JP, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published With international search report.</p>
<p>(54) Title: REACTIVE LIQUID CRYSTAL COMPOUNDS</p> <p>(57) Abstract</p> <p>The invention relates to reactive liquid crystal compounds of formula (I), wherein P, Sp, X, n, m, A¹, A², Z and R have the meaning given in claim 1, to compositions comprising reactive liquid crystal compounds of formula (I), to linear or cross-linked (co)polymers obtainable by (co)polymerizing said reactive liquid crystals or compositions and to the use of said reactive liquid crystals or compositions for the preparation of linear or cross-linked polymers or polymer films for decorative pigments, cosmetics or security applications, active and passive optical elements, colour filters, scattering displays, adhesives or synthetic resins with anisotropic mechanical properties.</p> <div style="text-align: center;"> $P-(\text{Sp-X})_n-A^1-(Z-A^2)_m-\text{COO}-\text{C}_6\text{H}_4-\text{C}_6\text{H}_4-\text{R} \quad (I)$ </div>		

FOR THE PURPOSES OF INFORMATION ONLY


Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Reactive Liquid Crystal Compounds

The invention relates to reactive liquid crystal compounds of formula I

5



wherein

10

P

is $\text{CH}_2=\text{CW}-\text{COO}-$, $\text{WCH}=\text{CH}-\text{O}-$, $\text{WHC}-\text{CH}-$ or $\text{CH}_2=\text{CH}-\text{Phenyl}-(\text{O})_k-$ with W being H, CH_3 or Cl and k being 0 or 1,

15

Sp

is a spacer group having 1 to 20 C atoms,

X

is $-\text{O}-$, $-\text{S}-$, $-\text{CO}-$, $-\text{COO}-$, $-\text{OCO}-$, $-\text{S-CO}-$, $-\text{CO-S}-$, $-\text{OCOO}-$ or a single bond,

20

n

is 0 or 1,

A¹ and A²

are each independently 1,4-phenylene in which, in addition, one or more CH groups may be replaced by N, 1,4-cyclohexenylene or 1,4-cyclohexylene in which, in addition, one or two non-adjacent CH₂ groups may be replaced by O and/or S, or naphthalene-2,6-diyl, it being possible for these rings to be substituted with halogen, cyano or nitro groups or with one or more alkyl, alkoxy or acyl groups with 1 to 7 C atoms wherein one or more H atoms may be substituted by F or Cl,

25

Z

is $-\text{OCO}-$, $-\text{COO}-$, $-\text{CH}_2\text{CH}_2-$, $-\text{CH}=\text{CH}-$, $-\text{C}\equiv\text{C}-$, $-\text{CH}_2\text{O}-$, $-\text{OCH}_2-$, or a single bond,

30

m

is 0 or 1, and

35

- R is an alkyl radical with up to 20 C atoms which may be unsubstituted, mono- or polysubstituted by halogen or CN, it being possible for one or more CH₂ groups to be replaced by -O-, -S-, -NH-, N(CH₃)-, -CO-, -OCO-, -COO-, -S-CO-, -CO-S-, -O-COO- in such a manner that oxygen atoms are not directly linked to one another, or alternatively R is halogen, cyano or has independently one of the meanings given for P-(Sp-X)_n.
- 10 The invention furthermore relates to compositions comprising at least two reactive liquid crystal compounds at least one of which is a compound of formula I as specified above.
- 15 Another aspect of the invention are linear or crosslinked (co)polymers obtainable by (co)polymerizing at least one reactive liquid crystal compound of formula I or a composition as described above.
- 20 Yet another aspect of the invention is the use of reactive liquid crystal compounds or compositions as described above for the preparation of linear or crosslinked polymers or polymer films for decorative pigments, cosmetics or security applications, active and passive optical elements, like e.g. optical polarizer or compensator films, colour filters, scattering displays, adhesives or synthetic resins with anisotropic mechanical properties.
- 25 Figure 1 shows the birefringence versus wavelength of a cured (1a) and an uncured (1b) composition according to the present invention.
- 30 Reactive liquid crystal compounds can be polymerized in situ when being macroscopically oriented in their liquid crystalline state to give anisotropic linear or crosslinked polymers and polymer films with a uniform orientation of high quality. Such materials can be used for example as optical elements like broad band cholesteric polarizers (see EP 0,606,940) or polarization filters (EP 0,397,263).
- 35

The European Application EP 0,451,905 describes scattering displays with anisotropic gels made of crosslinked diacrylates with phenyldibenzoate as mesogenic core and a low-molecular liquid crystalline material.

5

Reactive liquid crystal compounds of various molecular structures have been described in prior art. The WO 93/22397, EP 0,405,713 and DE 195,04,224 for example disclose reactive compounds with mesogenic cores consisting of phenylene, bi- or terphenylene or naphthalene ring systems linked by ester or ethylene groups and with terminal acrylate or epoxy groups as polymerizable groups.

10

The reactive liquid crystal compounds described in prior art, however, often exhibit liquid crystalline phases only in a small temperature range or do not show mesophase behaviour at all. Furthermore, they often have rather high melting points, which is in particular disadvantageous for the preparation of highly oriented anisotropic polymers, since the polymerization has then to be carried out at high temperatures. Another drawback of the reactive liquid crystal compounds of in prior art are their disadvantageous values of the birefringence.

15

20

For some applications it is useful to have anisotropic polymer films with good adhesion on plastic substrates. However, when polymerizing mixtures containing high amounts of reactive liquid crystal compounds with two polymerizable groups as disclosed in prior art, one obtains polymer films with high brittleness and poor adhesion.

25

There is therefore existing a demand for reactive liquid crystals with one polymerizable group to flexibilize mixtures and promote adhesion of the resulting polymer films.

30

Furthermore, regarding the broad range of applications for reactive liquid crystal compounds it is desirable for the expert to have available further compounds of this type which are easy to synthesize and fulfill the various requirements as described above.


35

It was therefore an aim of the invention to provide new reactive liquid crystal compounds with advantageous properties thus extending the pool of reactive liquid crystal compounds available to the expert. Other aims of the present invention are immediately evident to the person skilled in the art from the following detailed description.

The terms reactive mesogenic compound, reactive liquid crystal compound or reactive liquid crystalline compound as used in the foregoing and the following comprise compounds with a rodlike or boardlike mesogenic group. These compounds do not necessarily have to exhibit mesophase behaviour by themselves. It is also possible that they can show mesophase behaviour only in mixtures with other compounds or when the pure compounds or the mixtures are polymerized.

The object of the present invention are reactive liquid crystal compounds of formula I

20



wherein

25

P is $\text{CH}_2=\text{CW}-\text{COO}-$, $\text{WCH}=\text{CH}-\text{O}-$, $\text{WHC}-\text{CH}-$ or $\text{CH}_2=\text{CH}-\text{Phenyl}-(\text{O})_k-$ with W being H, CH_3 or Cl and k being 0 or 1,

30

Sp is a spacer group having 1 to 20 C atoms,

X

is $-\text{O}-$, $-\text{S}-$, $-\text{CO}-$, $-\text{COO}-$, $-\text{OCO}-$, $-\text{S-CO}-$, $-\text{CO-S}-$, $-\text{OCOO}-$ or a single bond,

35

n is 0 or 1,

- 5 A¹ and A² are each independently 1,4-phenylene in which, in addition, one or more CH groups may be replaced by N, 1,4-cyclohexenylene or 1,4-cyclohexylene in which, in addition, one or two non-adjacent CH₂ groups may be replaced by O and/or S, or naphthalene-2,6-diyl, it being possible for these rings to be substituted with halogen, cyano or nitro groups or with one or more alkyl, alkoxy or acyl groups with 1 to 7 C atoms wherein one or more H atoms may be substituted by F or Cl,
- 10 Z is -OCO-, -COO-, -CH₂CH₂-, -CH=CH-, -C≡C-, -CH₂O-, -OCH₂-, or a single bond,
- 15 m is 0 or 1, and
- 20 R is an alkyl radical with up to 20 C atoms which may be unsubstituted, mono- or polysubstituted by halogen or CN, it being possible for one or more CH₂ groups to be replaced by -O-, -S-, -NH-, N(CH₃)-, -CO-, -OCO-, -COO-, -S-CO-, -CO-S-, -O-COO- in such a manner that oxygen atoms are not directly linked to one another, or alternatively R is halogen, cyano or has independently one of the meanings given for P-(Sp-X)_n.
- 25 Another object of the present invention are compositions comprising at least two reactive liquid crystal compounds at least one of which is a compound of formula I.
- 30 Preferred embodiments of the invention are those wherein the reactive liquid crystalline compounds are compounds of formula I, wherein
- n is 1,
 - 35 • m is 0 and A¹ is 1,4-phenylene,

- 6 -

- Sp is alkylene with 1 to 15 C atoms,
- R is halogen, cyano or an optionally fluorinated achiral or chiral alkyl or alkoxy group with 1 to 15 C atoms.

5

In another preferred embodiment of the invention the reactive liquid crystalline compounds are selected according to formula I, wherein R has one of the meanings of P-(Sp-X)_n- given above.

10

In a further preferred embodiment the composition comprising reactive liquid crystalline compounds as described above is characterized in that it comprises at least one compound having two or more polymerizable terminal groups.

15

In a further preferred embodiment said composition is characterized in that it comprises at least one compound having a polymerizable terminal group and a chiral terminal group.

20

Another aspect of the invention are linear or crosslinked (co)polymers obtainable by (co)polymerizing at least one reactive liquid crystal compound of formula I or a composition as described above.

25

Yet another aspect of the invention is the use of reactive liquid crystal compounds or compositions as described above for the preparation of linear or crosslinked polymers or polymer films for decorative pigments, cosmetics or security applications, active and passive optical elements, like e.g. optical polarizer or compensator films, colour filters, anisotropic gels, scattering displays, adhesives or synthetic resins with anisotropic mechanical properties.

30


Formula I covers the tricyclic and tetracyclic compounds of the sub-formulae I 1 and I 2:

35



- 7 -

wherein MG denotes



5 Of the compounds of formula I 1 and I 2 especially preferred are those in which n is 1, R is alkyl or has the meaning given for P-Sp-X- and Z is -COO-, -OCO- or a single bond.

10 Of the mesogenic compounds which contain a heterocyclic group, those containing a pyridine-2,5-diyl group, pyrimidine-2,5-diyl group or 1,3-dioxane-2,5-diyl group are particularly preferred.

15 A smaller group of particularly preferred mesogenic compounds of the formulae I 1 and I 2 is listed below. For reasons of simplicity, PheS is 1,4-phenylene, which is substituted in 2- and/or 3-position with halogen, cyano or nitro groups or an alkyl, alkyloxy or acyloxy group having 1 to 7 C atoms wherein one or more H atoms may be substituted by F or Cl. Furthermore, Pyd is pyridine-2,5-diyl, Pyr is pyrimidine-2,5-diyl, Cyc is 1,4-cyclohexene, Dio is trans-1,3-dioxane-2,5-diyl and Dit is trans-1,3-dithiane-2,5-diyl. The notations Pyd, Pyr and Dio in each case include the two possible positional isomers.

Particularly preferred mesogenic compounds of the sub-formula I 1 are those of the sub-formulae I 1-1 to I 1-7:

25	P-Sp-X-Phe-MG-R	I 1-1
	P-Sp-X-PheS-MG-R	I 1-2
	P-Sp-X-Cyc-MG-R	I 1-3
	P-Sp-X-Pyd-MG-R	I 1-4
30	P-Sp-X-Pyr-MG-R	I 1-5
	P-Sp-X-Dio-MG-R	I 1-6
	P-Sp-X-Dit-MG-R	I 1-7

35 The compounds of formula I 1-1 to I 1-3 are preferred. In particular preferred are the compounds of formula I 1-1 and I 1-2.

Particularly preferred mesogenic compounds of the sub-formula I 2 are those of the sub-formulae I 2-1 to I 2-21:

	P-Sp-X-Phe-Z-Phe-MG-R	I 2-1
5	P-Sp-X-Phe-Z-PheS-MG-R	I 2-2
	P-SP-X-PheS-Z-PheS-MG-R	I 2-3
	P-Sp-X-Phe-Z-Cyc-MG-R	I 2-4
	P-Sp-X-Cyc-Z-Phe-MG-R	I 2-5
	P-Sp-X-Cyc-Z-PheS-MG-R	I 2-6
10	P-Sp-X-Cyc-Z-Cyc-MG-R	I 2-7
	P-Sp-X-Phe-Z-Pyd-MG-R	I 2-8
	P-Sp-X-Phe-Z-Pyr-MG-R	I 2-9
	P-Sp-X-Pyd-Z-Phe-MG-R	I 2-10
	P-Sp-X-Pyr-Z-Phe -MG-R	I 2-11
15	P-Sp-X-Pyd-Z-PheS-MG-R	I 2-12
	P-Sp-X-Pyr-Z-PheS-MG-R	I 2-13
	P-Sp-X-Phe-Z-Dio-MG-R	I 2-14
	P-Sp-X-Dio-Z-Phe-MG-R	I 2-15
	P-Sp-X-Dio-Z-PheS-MG-R	I 2-16
20	P-Sp-X-Phe-Z-Dit-MG-R	I 2-17
	P-Sp-X-Dit-Z-Phe-MG-R	I 2-18
	P-Sp-X-Dit-Z-PheS-MG-R	I 2-19
	P-Sp-X-Dio-Z-Dit-MG-R	I 2-20
	P-Sp-X-Dit-Z-Dio-MG-R	I 2-21
25		

Of these compounds, those of formula I 2-1 to I 2-13 are preferred. Especially preferred are the compounds of formula I 2-1 to I 2-7, in particular those of formula I 2-1, I 2-2, I 2-4 and I 2-5.

30 Of the preferred compounds of formulae I 2-1 to I 2-21 in particular preferred are those in which Z is an ester group (-COO- or -OCO-), -CH₂-CH₂- or a single bond.


35 Of the preferred compounds containing a substituted 1,4-phenylene group very particularly preferred are those substituted by F, Cl or methyl.

In the mesogenic compounds of the formula I, R is preferably an alkyl radical which is unsubstituted or substituted by at least one halogen atom, it being possible for one or two non-adjacent CH₂ groups of these radicals to be replaced by -O-, -S-, O-CO-, -CO-O- or -O-CO-O- groups. Halogen is preferably F or Cl.

If R is an alkyl or alkoxy radical, i.e. where the terminal CH₂ group is replaced by -O-, this may be straight-chain or branched. It is preferably straight-chain, has 2, 3, 4, 5, 6, 7 or 8 carbon atoms and accordingly is preferably ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, ethoxy, propoxy, butoxy, pentoxy, hexoxy, heptoxy, or octoxy, furthermore methyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, methoxy, nonoxy, decoxy, undecoxy, dodecoxy, tridecoxy or tetradecoxy, for example.

Oxaalkyl, i.e. where one CH₂ group is replaced by -O-, is preferably straight-chain 2-oxapropyl (=methoxymethyl), 2- (=ethoxymethyl) or 3-oxabutyl (=2-methoxyethyl), 2-, 3-, or 4-oxapentyl, 2-, 3-, 4-, or 5-oxahexyl, 2-, 3-, 4-, 5-, or 6-oxaheptyl, 2-, 3-, 4-, 5-, 6- or 7-oxaoctyl, 2-, 3-, 4-, 5-, 6-, 7- or 8-oxanonyl or 2-, 3-, 4-, 5-, 6-, 7-, 8- or 9-oxadecyl, for example.

R may be an achiral or a chiral group. In case of a chiral group it is preferably selected according to formula II:



wherein

X has the meaning given above,

Q¹ is an alkyl or alkoxy group with 1 to 7 C atoms or a single bond,

Q² is an alkyl or alkoxy group with 1 to 8 C atoms which may be unsubstituted, mono- or polysubstituted by halogen or CN, it being also possible for one or more non-adjacent CH₂ groups to be replaced, in each case independently from one another, by -O-, -S-,
5 -NH-, -N(CH₃)-, -CO-, -COO-, -OCO-, -OCO-O-, -S-CO- or -CO-S- in such a manner that oxygen atoms are not linked directly to one another, or has the meaning given for P-Sp-,

10 Q³ is halogen, a cyano group or an alkyl or alkoxy group with 1 to 4 C atoms different from Q².

Preferred chiral groups are 2-butyl (=1-methylpropyl), 2-methylbutyl, 2-methylpentyl, 3-methylpentyl, 2-ethylhexyl, 2-propylpentyl, 2-octyl, in particular 2-methylbutyl, 2-methylbutoxy, 2-methylpentoxy, 3-
15 methylpentoxy, 2-ethylhexoxy, 1-methylhexoxy, 2-octyloxy, 2-oxa-3-methylbutyl, 3-oxa-4-methylpentyl, 4-methylhexyl, 2-nonyl, 2-decyl, 2-dodecyl, 6-methoxyoctoxy, 6-methyloctoxy, 6-methyloctanoyloxy, 5-methylheptyloxycarbonyl, 2-methylbutyryloxy, 3-methylvaleryloxy, 4-methylhexanoyloxy, 2-chloropropionyloxy, 2-chloro-3-
20 methylbutyryloxy, 2-chloro-4-methylvaleryloxy, 2-chloro-3-methylvaleryloxy, 2-methyl-3-oxapentyl, 2-methyl-3-oxahexyl, 1-methoxypropyl-2-oxy, 1-ethoxypropyl-2-oxy, 1-propoxypropyl-2-oxy, 1-butoxypropyl-2-oxy, 2-fluorooctyloxy, 2-fluorodecyloxy, for example.


25 In addition, mesogenic compounds of the formula I containing an achiral branched group R may occasionally be of importance as comonomers, for example, due to a reduction in the tendency towards crystallization. Branched groups of this type generally do not
30 contain more than one chain branch. Preferred achiral branched groups are isopropyl, isobutyl (=methylpropyl), isopentyl (=3-methylbutyl), isopropoxy, 2-methylpropoxy and 3-methylbutoxy.

35 In another preferred embodiment the chiral group is selected from the following groups:

- 11 -


a cholesteryl group,

5



10


an ethylenglycol derivative



wherein R¹ is an alkyl radical with 1 to 12 C atoms,


15

a terpenoid radical like, for example, menthol



20

or a group based on citronellol




25


In the compounds of formula I P is $\text{CH}_2=\text{CW}-\text{COO}$, $\text{WHC}-\text{CH}_2-\text{CH}-$
 $\text{WCH}=\text{CH}-\text{O}-$ or $\text{CH}_2=\text{CH}-\text{Phenyl}-(\text{O})_k-$ with W being H, CH₃ or Cl
 and k being 0 or 1.

30

Preferably P is a vinylether or propenylether group, an acrylate or
 methacrylate group or an epoxy group. Especially preferred are the
 following meanings of P:




acrylate



methacrylate

35

- 12 -



epoxy group

5 As for the spacer group Sp all groups can be used that are known for this purpose to the skilled in the art. The spacer group is preferably linked to the polymerizable group P by an ester or ether group or a single bond. It is preferably a linear or branched alkylene group having 1 to 20 C atoms, in particular 1 to 12 C atoms, in which, in addition, one or more non-adjacent CH₂ groups may be replaced by -

10 O-, -S-, -NH-, -N(CH₃)-, -CO-, -O-CO-, -S-CO-, -O-COO-, -CO-S-, -CO-O-, -CH(halogen)-, -CH(CN)-, -CH=CH- or -C≡C-.

Typical spacer groups are for example -(CH₂)_o-, -(CH₂CH₂O)_r-, CH₂CH₂-, -CH₂CH₂-S-CH₂CH₂- or -CH₂CH₂-NH-CH₂CH₂-, with o being an integer from 2 to 12 and r being an integer from 1 to 3.

15

Preferred spacer groups are ethylene, propylene, butylene, pentylene, hexylene, heptylene, octylene, nonylene, decylene, undecylene, dodecylene, octadecylene, ethyleneoxyethylene, methyleneoxybutylene, ethylene-thioethylene, ethylene-N-methyl-iminoethylene and 1-methylalkylene, for example.

20

In particular preferred are compounds of formula I wherein n is 1.

25

In another preferred embodiment, the polymers are copolymers obtained by copolymerizing mixtures comprising compounds of formula I wherein n is 0 and compounds of formula I wherein n is 1.

30 In the event that R or Q² is a group of formula P-Sp-X- or P-Sp- respectively, the spacer groups on each side of the mesogenic core may be identical or different.

Anisotropic polymers can be prepared by solution polymerization or by in-situ polymerization. Solution polymerization can be carried out for example in a solvent like dichloromethane, tetrahydrofuran or

35

5 toluene using AIBN as an initiator and heating for 24 hours at 30 to 60 °C. However, in order to obtain polymers with macroscopic uniform orientation, the polymers prepared by solution polymerization have to be aligned afterwards by special means like electric or magnetic fields and high temperatures.

10 On the other hand, mesogenic monomers like the inventive compounds can easily be aligned by conventional techniques and the alignment can subsequently be frozen in by in-situ polymerization. A detailed description of this method can be found in D.J.Broer et al., Makromol.Chem. 190, 2255ff. and 3202ff. (1989).

15 The reactive liquid crystal compounds and compositions according to this invention are preferably polymerized in situ as described in the foregoing and the following.

20 Polymerization of reactive mesogenic compounds or compositions comprising compounds with only one polymerizable functional group leads to linear polymers or copolymers, whereas in the presence of compounds with more than one polymerizable functional group crosslinked polymers are obtained.

25 In particular crosslinked polymers show very high thermal stability of the optical and mechanical properties, depending on the degree of crosslinking, when compared to linear polymers.

30 Linear or crosslinked polymers or copolymers are obtained for example by exposure of the inventive reactive liquid crystal compounds or compositions to actinic radiation in the presence of an initiator having an absorption maximum adjusted to the wavelength of said radiation.

35 For example, one can use UV light and a photoinitiator that decomposes under UV irradiation to produce free radicals that start the polymerization reaction. In another preferred embodiment a cationic photoinitiator is used that photocures with cations instead of

free radicals. The polymerization may also be started by an initiator that decomposes when heated above a certain temperature.

5 As a photoinitiator for example the commercially available Irgacure 651 (from Ciba Geigy AG) can be used.

10 Polymerization of reactive liquid crystal compounds or compositions comprising compounds with only one polymerizable functional group leads to linear polymers or copolymers, whereas in the presence of compounds with more than one polymerizable functional group crosslinked polymers are obtained.

15 In addition to light- or temperature-sensitive initiators said compositions may also comprise one or more other suitable components such as, for example, catalysts, stabilizers, co-reacting monomers or surface-active compounds.

20 It is alternatively possible to add, for example, a quantity of up to 20% by weight of a nonpolymerizable liquid-crystalline material to adapt the optical properties of the polymer.

25 It is also possible to add up to 20% of a non mesogenic compound with two or more polymerizable functional groups to increase crosslinking of the polymers. Typical examples for difunctional non mesogenic monomers are alkyldiacrylates or alkyldimethacrylates with alkyl groups of 1 to 20 C atoms. Typical examples for non mesogenic monomers with more than two polymerizable groups are trimethylpropanetrimethacrylate or pentaerythritoltetraacrylate.

30 To prepare anisotropic polymer films with uniform orientation the inventive reactive liquid crystal compounds or compositions, for example, are coated onto a substrate, aligned and cured by irradiating as described above. Alignment and curing are hereby carried out in the mesophase of the reactive liquid crystal compounds.

35

As a substrate for example a glass plate or a plastic film can be used. To achieve uniform alignment, the film can be sheared for example by means of a doctor's blade. In another preferred embodiment, a second substrate is put on top of the coated material. In this case, the shearing caused by putting together the two substrates is sufficient to give good alignment.

In some embodiments it is of advantage to apply a second substrate in order to exclude oxygen that may inhibit the polymerization. Alternatively the curing can be carried out under a nitrogen atmosphere. In the latter case shearing of the mesogenic material prior to polymerization is necessary to cause sufficient alignment of the mesophase. When using a cationic photoinitiator oxygen exclusion is not needed, but water should be excluded.

The compounds of the present invention can be used in mixtures with other reactive liquid crystal compounds to give mixtures with low melting points. This is of importance especially when anisotropic polymer films are prepared. To obtain highly oriented films the polymerization has to be carried out in the liquid crystal phase of the reactive liquid crystal mixture. Thus by using the compounds of this invention the polymerization temperature can be lowered significantly and the polymerization process is made easier.

Another object of the invention is to provide compounds for polymer films with good adhesion to plastic substrates. Crosslinked anisotropic polymers made from mixtures containing high amounts of reactive liquid crystal compounds with two functional polymerizable groups exhibit a good heat resistance. On the other hand, with increasing amount of the difunctional reactive liquid crystal compounds the brittleness of the polymer is increasing and the adhesion to substrates is decreasing.

Thus a special preferred embodiment of the invention are compounds of formula I, wherein R is an achiral alkyl or alkoxy

group, used for the preparation of polymers in order to balance the heat resistance and the adhesion of the resulting polymer films.

5 Another preferred embodiment of the invention is a mixture comprising at least two reactive liquid crystal compounds at least one of which is a compound as described in the previous paragraph, characterized in that the mixture contains not more than 20% of a compound having two or more polymerizable groups.

10 The reactive liquid crystal compounds according to formula I can be prepared by methods which are known per se and which are described, for example, in standard works of organic chemistry such as, for example, Houben-Weyl, Methoden der organischen Chemie, Thieme-Verlag, Stuttgart. Some specific methods of preparation can
15 be taken from the examples.

Without further elaboration, it is believed that one skilled in the art can, using the preceding description, utilize the present invention to
20 its fullest extent. The following examples are, therefore, to be construed as merely illustrative and not limitative of the remainder of the disclosure in any way whatsoever.

The entire disclosure of all applications, patents and publications, cited above and below, are hereby incorporated by reference.

25 In the foregoing and in the following examples, all temperatures are set forth uncorrected in degrees Celsius and unless otherwise indicated, all parts and percentages are by weight. The following abbreviations are used to illustrate the liquid crystalline phase
30 behaviour of the compounds:

C = crystalline; N = nematic; S = smectic; S_A = smectic A; Ch = cholesteric; I = isotropic. The numbers between these symbols indicate the phase transition temperatures in degree Celsius.

35


The following abbreviations are used:

	DMF	dimethylformamide
	DCM	dichloromethane
5	DCCI	dicyclohexylcarbodiimide


Examples

10 Example 1

The reactive liquid crystal compounds of formula (3)



are prepared according to the following reaction scheme:



35 The synthesis of the benzoic acid (1) is disclosed in D.J.Broer et al., Makromol.Chem. **190**, 2255 (1989). The phenol (2) can be prepared in an analogous manner to the compounds described in DE 2,636,684.

The compounds (1) exhibit the following mesophase behaviour:

5	No.	x	y	phase behaviour
	3a	6	3	C 66 N 154 I
	3b	6	4	C 74 N 186 I
	3c	6	5	C 74 S 102 N 151 I
	3d	3	5	C 90 N 163 I
	3e	3	7	C 68 N 164 I
10	3f	3	3	C 88 N 171 I
	3g	3	4	C 98 N 160 I

Example 2

15

A mixture is formulated consisting of

compound (3a) 60%

compound (3f) 40%

20

The mixture exhibits the mesophase behaviour C 43 N 160 I with a significantly low melting point.

Example 3

25

A mixture is formulated consisting of


compound (3a) 27%

compound (3f) 18%

30

compound (4) 55%

35




The preparation of compound (4) is described in DE 195,04,224. The mixture is melting below room temperature and exhibits the mesophase behaviour S_A 24.4 Ch 67 I. The mixture is cured between two glass slides by exposure to UV light at a temperature of 35 °C. A cholesteric copolymer is formed with a glass transition temperature T_g of 1.8 °C and a reflection wavelength of 549 nm.

Example 4

The following mixtures are formulated:

	4A	4B	4C	4D
compound (3a)	25.2%	23.4%	20.4%	17.4%
compound (3f)	16.8%	15.6%	13.6%	11.6%
compound (4)	55%	55%	55%	55%
compound (5)	2%	5%	10%	15%
Irgacure 651	1%	1%	1%	1%



(5)

The di reactive compound (5) can be prepared as described in WO 93/22397 and serves as crosslinking agent to increase T_g and thereby the brittleness of the polymer. Irgacure 651 is a commercially available photoinitiator from Ciba Geigy AG, Basel, Switzerland.

The mixtures exhibit the following mesophase behaviour:

4A	S_A 22 Ch 66.1 I
4B	S_A 19 Ch 64.8 I
4C	S_A 14 Ch 62.9 I
4D	S_A 9 Ch 60.0 I


The mixtures are put between two glass slides coated with a layer of rubbed polyimide and cured by exposure to UV light in the cholesteric phase at temperatures of 35 to 40 °C. The resulting polymer films exhibit the following values for T_g and the reflection wavelength λ while showing different quality of adhesion when put on a plastic substrate:

	4A	4B	4C	4D
T _g (°C)	4	6	10	12
λ (nm)	548	540	534	524
content of (5)	2%	5%	10%	15%


When going from 4D to 4A, the adhesion of the films is improving with decreasing amount of directive compound (5). In the same direction the polymer films become more flexible, as is indicated by the decrease of T_g.


Example 5

The reactive liquid crystal compounds of formula (6)



are prepared by the following synthetic route:






15 The following compounds were prepared and their mesophase behaviour was investigated:


No.	n	R	phase behaviour
6a	9	C_3H_7	C 74 N 166 I
6b	9	C_4H_9	C 87 N 161 I
20 6c	9	C_5H_{11}	C 71 S _A 102 N 165 I


Example 6

25 The reactive liquid crystal compounds of formula (7)



30 are prepared by the following synthetic route:






20 The compound with $n = 8$ and $\text{R} = \text{C}_4\text{H}_9$ exhibits the mesophase behaviour C 68 N 167 I.

Example 7

25 The following mixture was formulated

30	compound (3a)	40.1 %
	compound (3f)	29.2 %
	compound (5)	22.6 %
	compound (8)	3.4 %
	Irgacure 907	4.0 %



Irgacure is a photoinitiator available from Ciba Geigy AG.

5 The diactive compound (8) can be prepared as described in WO 93/22397.


10 The mixture exhibits the mesophase behaviour C 40 N 138 I but supercools to room temperature without crystallization. The optical anisotropy Δn is 0.157, measured at 20 °C with light of a wavelength of 600 nm.

15 The mixture is homogeneously aligned between two glass slides and cured by exposure to UV light at 20 °C to give a polymer film with a birefringence of 0.144 (600 nm, 20 °C). The variation of the birefringence versus wavelength is shown in Figure 1a for the cured and in Figure 1b for the uncured mixture.

20 Example 8

The following mixture was formulated

25	compound (3a)	65 %
	compound (5)	5 %
	compound (9)	30 %



30

The preparation of compound (9) is described for example in M. Portugall et al., Makromol. Chem. **183**, 2311 (1982).

35

The mixture has the mesophase behaviour C 30 S_A 55 N 114 I.

Example 9

The following mixture was formulated

5	compound (3a)	35 %
	compound (3c)	30 %
	compound (5)	5 %
	compound (9)	30 %

10 The mixture has the mesophase behaviour C 30 S_A 62 N 107 I.

15

20

25


30

35

Patent Claims

1. Reactive liquid crystal compound of formula I

5



10

wherein

P is $\text{CH}_2=\text{CW}-\text{COO}-$, $\text{WCH}=\text{CH}-\text{O}-$, $\text{WHC}-\text{CH}-$ or $\text{CH}_2=\text{CH}-\text{Phenyl}-(\text{O})_n-$ with W being H, CH_3 or Cl and n being 0 or 1,

15

Sp is a spacer group having 1 to 20 C atoms,

X is $-\text{O}-$, $-\text{S}-$, $-\text{CO}-$, $-\text{COO}-$, $-\text{OCO}-$, $-\text{O}-\text{COO}-$, $-\text{S}-\text{CO}-$, $-\text{CO}-\text{S}-$ or a single bond,

20

n is 0 or 1,

25

A^1 and A^2 are each independently 1,4-phenylene in which, in addition, one or more CH groups may be replaced by N, 1,4-cyclohexenylene or 1,4-cyclohexylene in which, in addition, one or two non-adjacent CH_2 groups may be replaced by O and/or S, or naphthalene 2,6-diyl, it being possible for these rings to be substituted with halogen, cyano or nitro groups or with one or more alkyl, alkoxy or acyl groups with 1 to 7 C atoms wherein one or more H atoms may be substituted by F or Cl,

30

Z is $-\text{OCO}-$, $-\text{COO}-$, $-\text{CH}_2\text{CH}_2-$, $-\text{CH}=\text{CH}-$, $-\text{C}\equiv\text{C}-$, $-\text{CH}_2\text{O}-$, $-\text{OCH}_2-$, or a single bond,

35

m is 0 or 1, and

R is an alkyl radical with up to 20 C atoms which may be unsubstituted, mono- or polysubstituted by halogen or CN, it being possible for one or more CH₂ groups to be replaced by -O-, -S-, -NH-, N(CH₃)-, -CO-, -OCO-, -COO-, -S-CO-, -CO-S-, -O-COO- in such a manner that oxygen atoms are not directly linked to one another, or alternatively R is halogen, cyano or has independently one of the meanings given for P-(Sp-X)_n.

2. A reactive liquid crystalline compound of claim 1, wherein n is 1, m is 0 and A¹ is 1,4-phenylene.
3. A reactive liquid crystalline compound of claim 1 or 2, wherein n is 1 and Sp is alkylene with 1 to 15 C atoms.
4. A reactive liquid crystalline compound of claim 1, 2 or 3, wherein R is halogen, cyano or an optionally fluorinated achiral or chiral alkyl or alkoxy group with 1 to 15 C atoms.
5. A reactive liquid crystalline compound of claim 1, 2 or 3, wherein R has one of the meanings given for P-(Sp-X)_n.
6. A composition comprising at least two reactive liquid crystalline compounds characterized in that at least one of which is a compound of formula I according to claims 1 to 5.
7. A composition according to claim 6 characterized in that it comprises at least one compound having two polymerisable terminal groups.



8. A composition according to claim 6 or 7 characterized in that it comprises at least one compound having a polymerisable terminal group and a chiral terminal group.
- 5 9. A linear or crosslinked (co)polymer obtainable by (co)polymerizing at least one monomer or a composition according to any of the preceding claims.
- 10 10. Use of reactive liquid crystalline compounds or compositions as described in claim 1 to 8 for the preparation of polymers or polymer films for decorative pigments, cosmetics or, security applications, active and passive optical elements, like e.g. optical polarizer or compensator films, colour filters, scattering displays, adhesives or synthetic resins with anisotropic mechanical properties.
- 15

20

25

30

35

Figure 1**(a)****(b)**

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 97/00843

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C07C69/54 C07C69/78 C07C69/96 C07C69/533 C07D303/22
C07D303/40 C09K19/30 C09K19/38 C08F20/18 C08G59/20
C08G59/22

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C07C C07D C08F C08G C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 659 865 A (DAINIPPON INK AND CHEMICALS, INC.) 28 June 1995 see claims 2,19 ---	1-3
A	DE 195 04 224 A (MERCK PATENT GMBH) 24 August 1995 cited in the application see claims ---	1,8-10
A	WO 93 22397 A (MERCK PATENT GMBH) 11 November 1993 cited in the application see examples ---	1
A	EP 0 397 263 A (N. V. PHILIPS' GLOEILAMPENFABRIEKEN) 14 November 1990 cited in the application see page 5, line 20 - page 6, line 35 ---	1
-/-		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

6 June 1997

Date of mailing of the international search report

18.06.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Hass, C

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 97/00843

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 606 940 A (PHILIPS ELECTRONICS N. V.) 20 July 1994 cited in the application see figures 2A,2B ---	1
A	EP 0 451 905 A (N. V. PHILIPS' GLOEILAMPENFABRIEKEN) 16 October 1991 cited in the application see page 9, formula 14 ---	1
A	EP 0 168 683 A (F. HOFFMANN-LA ROCHE & CO. AG) 22 January 1986 see claims 1-6,11 ---	1
A	EP 0 315 050 A (F. HOFFMANN-LA ROCHE & CO. AG) 10 May 1989 see page 6, formula XVI, page 7, lines 9-10 ---	1
A	EP 0 331 933 A (F. HOFFMANN-LA ROCHE & CO. AG) 13 September 1989 see page 6, formula IV; page 7, lines 14, 15, 16 ---	1
A	EP 0 261 614 A (F. HOFFMANN-LA ROCHE & CO. AG) 30 March 1988 see claims 1,8 ---	1
A	DE 26 36 684 A (MERCK PATENT GMBH) 16 February 1978 cited in the application ---	
A	DIE MAKROMOLEKULARE CHEMIE, vol. 190, no. 9, 1989, pages 2255-2268, XP000330152 D. J. BROER ET AL.: "In-situ photopolymerization of oriented liquid-crystalline acrylates, 3. Oriented polymer networks from a mesogenic diacrylate" cited in the application ---	
A	DIE MAKROMOLEKULARE CHEMIE, vol. 183, no. 10, 1982, pages 2311-2321, XP000248168 M. PORTUGALL ET AL.: "Synthesis and Phase Behaviour of Liquid Crystalline Polyacrylates" cited in the application -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 97/00843

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 659865 A	28-06-95	JP 7294735 A	10-11-95
		JP 7294940 A	10-11-95
		JP 8021915 A	23-01-96
		JP 8027066 A	30-01-96
		JP 8029618 A	02-02-96
		JP 8041461 A	13-02-96
		JP 8092556 A	09-04-96
		JP 8003111 A	09-01-96
		JP 8075924 A	22-03-96
DE 19504224 A	24-08-95	JP 7258638 A	09-10-95
		US 5560864 A	01-10-96
WO 9322397 A	11-11-93	EP 0591508 A	13-04-94
		JP 6507987 T	08-09-94
EP 397263 A	14-11-90	NL 8901167 A	03-12-90
		DE 69015249 D	02-02-95
		DE 69015249 T	20-07-95
		JP 3021904 A	30-01-91
		US 5024850 A	18-06-91
EP 606940 A	20-07-94	CN 1095164 A	16-11-94
		JP 6281814 A	07-10-94
		US 5506704 A	09-04-96
EP 451905 A	16-10-91	NL 9000808 A	01-11-91
		JP 4227684 A	17-08-92
		US 5188760 A	23-02-93
EP 168683 A	22-01-86	HK 91892 A	27-11-92
		JP 7002653 B	18-01-95
		JP 61083136 A	26-04-86
		US 5238602 A	24-08-93
EP 315050 A	10-05-89	DE 3883705 D	07-10-93
		HK 33195 A	17-03-95
		JP 1151531 A	14-06-89
		SG 181194 A	12-05-95
		US 5013477 A	07-05-91

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 97/00843

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 331933 A	13-09-89	JP 1261494 A	18-10-89
EP 261614 A	30-03-88	JP 63101482 A	06-05-88
DE 2636684 A	16-02-78	AT 351618 B	10-08-79
		CH 631737 A	31-08-82
		CH 630111 A	28-05-82
		FR 2361353 A	10-03-78
		GB 1531405 A	08-11-78
		HK 50379 A	03-08-79
		JP 1580781 C	11-10-90
		JP 63038341 B	29-07-88
		JP 63066144 A	24-03-88
		JP 1620490 C	09-10-91
		JP 63038342 B	29-07-88
		JP 63088156 A	19-04-88
		JP 1095874 C	14-05-82
		JP 53023957 A	06-03-78
		JP 56038146 B	04-09-81
		JP 1456539 C	09-09-88
		JP 54095985 A	28-07-79
		JP 62061636 B	22-12-87
		NL 7708929 A,C	16-02-78
		SU 906387 A	15-02-82
		US 4130502 A	19-12-78

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.